

Tannin™ Has It.

LIONPROOF SR-60

tannincorp.com

COMPOSITION

A silicone emulsion for use in waterproof systems. For best results, it should be fixed with a metal salt after application.

SPECIFICATIONS

Appearance	White liquid / paste
Activity	55% – 65%
Charge	Anionic
Density (Lb/Gal)	7.5 – 8.5
pH (10% Solution)	7.0 – 9.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Sensitive to freezing. Do not store below 5°C.
Lightfastness	Good
Electrolyte Stability	Good
Emulsification	Mix before use. Readily soluble in warm water. Mix 1:1 with warm water until homogeneous. Emulsify to 1:4 at 30°C to 60°C.

KEY PROPERTIES

LIONPROOF SR-60 is normally used in waterproof systems together with other hydrophobic products to give water resistance and enhance Maeser flexes.

- Waterproofing emulsion for chrome tanned leathers
- High Maeser flexes achieved
- Promotes low water absorption
- Can be used on dyed or white leathers
- Used as a topping oil to increase surface water resistance

APPLICATIONS

Recommended usage is 2% to 4% on Blue shaved weight.



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx