Tannin" Has It. LIONSOFT SF-1200

tannincorp.com

COMPOSITION

A medium blown, bisulfited fish oil.

SPECIFICATIONS

Appearance Activity Charge Density (Lb/Gal) pH (10% Solution) Storage Stability

Freeze/Thaw Stability

Lightfastness Electrolyte Stability Emulsification

Amber liquid 88% (± 2) Anionic 8.2 (± 0.2) 6.0 - 8.0One year at room temperature. Optimum storage temperature is between 15°C and 30°C. Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous. Good Very Good Mix before use. Readily soluble in warm water. Emulsify 1:4 at 50°C to 60°C.

KEY PROPERTIES

LIONSOFT SF-1200 is normally used in making soft leathers such as upholstery, garment, and milled shoe upper leathers.

- An excellent penetrating oil and co-product with other fatliquors
- Excellent stability in Chrome retanning and hard water applications
- Imparts excellent tensile strength
- Aids in penetration and softening action of other fatliquors

APPLICATIONS

Recommended usage is 2% to 14% on Blue shaved weight.





Tannin Corporation 65 Walnut Street Peabody, MA 01960, USA Phone: +1.978.532.4010 Fax: +1.978.532.5536 sales@tannincorp.com Tannin Mexico S.A. de C.V. Blvd. San Crispin 130 Fracc. Ind. San Crispin Leon, Gto. 37527, Mexico teléfono: +52.477.770.9499 tanninmex@terra.com.mx

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.