Tannin Has It. LIONSOFT SN-230

tannincorp.com

COMPOSITION

A medium blown, bisulfited neatsfoot oil.

SPECIFICATIONS

Appearance Yellow liquid Activity $65\% (\pm 2)$ Charge Anionic Density (Lb/Gal) $8.0 (\pm 0.2)$ pH (10% Solution) 6.0 - 8.0

Storage Stability One year at room temperature.

Optimum storage temperature is

between 15°C and 30°C.

Freeze/Thaw Stability Not sensitive to freezing.

After freezing heat to 25°C to 30°C and

mix well until homogeneous.

Lightfastness Good
Heatfastness Very Good
Electrolyte Stability Very Good

KEY PROPERTIES

LIONSOFT SN-230 is normally used in making soft leathers such as upholstery, garment, bag, nappa, and shoe upper leathers.

- An excellent penetrating oil and co-product with other fatliquors
- Good stability in Chrome retanning and hard water applications
- Imparts excellent tensile strength
- Aids in penetration and softening action of other fatliguors
- Excellent filling properties with a soft, tight handle

APPLICATIONS

Recommended usage is 2% to 12% on Blue shaved weight.





Tannin Corporation 65 Walnut Street Peabody, MA 01960, USA Phone: (978) 532-4010 Fax: (978) 532-5536 sales@tannincorp.com Tannin Mexico S.A. de C.V. Blvd. San Crispin 130 Fracc. Ind. San Crispin Leon, Gto. 37527, Mexico tanninmex@terra.com.mx