



COMPOSITION

A cationic topping and stuffing wax blend made from natural and petroleum-based components.

SPECIFICATIONS

Appearance	White paste
Activity	50% (± 2)
Charge	Cationic
Density (Lb/Gal)	7.8 (± 0.2)
pH (10% Solution)	4.0 – 5.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Sensitive to freezing. Do not store below 5°C.
Lightfastness	Good
Electrolyte Stability	Good
Emulsification	Mix before use. Readily soluble in warm water. Mix 1:1 with warm water until homogeneous. Emulsify to 1:4 at 30°C to 60°C.

KEY PROPERTIES

MARDOL 1156-CF is used as a topping oil to achieve a rich, waxy surface feel and to accomplish plate release during drying. In larger amounts it is used as a stuffing wax to make pull-up and semi-stuffed leathers.

- Imparts a waxy feel to the leather surface
- Excellent plate release during drying
- Develops stuffed leathers at higher concentrations

APPLICATIONS

Recommended usage is 2% to 8%.

tannincorp.com



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx