



## COMPOSITION

A sulfated marine and emulsified mineral oil blend.

## SPECIFICATIONS

Appearance	Amber liquid
Activity	90% ( $\pm 2$ )
Charge	Anionic
Density (Lb/Gal)	7.8 ( $\pm 0.2$ )
pH (10% Solution)	6.0 – 8.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. Do not store below 5°C.
Lightfastness	Fair
Electrolyte Stability	Fair
Emulsification	Mix before use. Readily soluble in warm water. Emulsify to 1:4 at 30°C to 60°C.

## KEY PROPERTIES

**MARDOL 1507** is a compound for an intermediate oiling of vegetable leather during the wetback and drying operation. It promotes good grain lubrication for the subsequent rolling of sole leather bends.

- Excellent grain lubrication
- Promotes rich draggy feel
- Promotes color development of black and dark dyeings

## APPLICATIONS

Recommended usage is 2% to 6%.

[tannincorp.com](http://tannincorp.com)



Tannin Corporation  
65 Walnut Street  
Peabody, MA 01960, USA  
Phone: +1.978.532.4010  
Fax: +1.978.532.5536  
sales@tannincorp.com

Tannin Mexico S.A. de C.V.  
Blvd. San Crispin 130  
Fracc. Ind. San Crispin  
Leon, Gto. 37527, Mexico  
teléfono: +52.477.770.9499  
tanninmex@terra.com.mx