



COMPOSITION

A concentrated blend of natural and synthetic oils and waxes emulsified with cationic emulsifiers.

SPECIFICATIONS

Appearance	Brown solid
Activity	100% (± 2)
Charge	Cationic
Density (Lb/Gal)	7.0 (± 0.2)
pH (10% Solution)	4.0 – 5.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Fair
Electrolyte Stability	Good
Emulsification	Melt to 70°C before use. Emulsify 1:4 at 65 - 70°C. Mix well before adding to drum.

KEY PROPERTIES

MARDOL 1583 used as a single component cationic based stuffing wax for use in making stuffed or semi-stuffed leathers on both pasted and vacuum dried full grain and corrected leathers.

- An excellent single component pull-up wax
- Good holding properties for finish oil & wax applications
- Excellent emulsification and uniform distribution

APPLICATIONS

Recommended usage at 4% - 16%.

tannincorp.com



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx