



COMPOSITION

A sulfated neatsfoot oil.

SPECIFICATIONS

Appearance	Light amber liquid
Activity	75% (± 2)
Charge	Anionic
Density (Lb/Gal)	8.0 (± 0.2)
pH (10% Solution)	6.0 – 8.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Good
Electrolyte Stability	Fair
Emulsification	Mix before use. Readily soluble in warm water. Emulsify 1:4 at 50°C to 60°C.

KEY PROPERTIES

MARDOL 722 is an excellent all purpose oil for use in making numerous types of leathers where a round handle and tight grain are required.

- Full, round temper
- Excellent grain lubrication
- Good softness without looseness
- General purpose sulfated oils

APPLICATIONS

Recommended usage is 2% to 6%.

tannincorp.com



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: (978) 532-4010
Fax: (978) 532-5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
tanninmex@terra.com.mx