



MARDEN-WILD CORPORATION

MARDOL BS-084

COMPOSITION

A medium-blown, bisulfited fish oil.

SPECIFICATIONS

Appearance	Amber liquid
Activity	84% (± 2)
Charge	Anionic
Density (Lb/Gal)	8.0 (± 0.2)
pH (10% Solution)	6.0 – 8.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Good
Electrolyte Stability	Very Good
Emulsification	Mix before use. Readily soluble in warm water. Emulsify 1:4 at 50°C to 60°C.

KEY PROPERTIES

MARDOL BS-084 is normally used in making soft leathers such as upholstery, garment, and milled shoe upper leathers.

- An excellent penetrating oil and co-product with other fatliquors
- Excellent stability in Chrome retanning and hard water applications
- Imparts excellent tensile strength
- Aids in penetration and softening action of other fatliquors
- Good resistance to heat and light
- Excellent softness and fixation

APPLICATIONS

Recommended usage at 2% - 16%.

tannincorp.com



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.