



MARDEN-WILD CORPORATION

MARDOL WT-47

COMPOSITION

A concentrated anionic blend of sulfated oils, degreas, and petroleum oils and waxes.

SPECIFICATIONS

Appearance	Brown solid
Activity	93% (± 2)
Charge	Anionic
Density (Lb/Gal)	7.5 (± 0.2)
pH (10% Solution)	5.0 – 7.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing.
Lightfastness	Good
Electrolyte Stability	Fair
Emulsification	Melt to 60°C then mix before use. Readily soluble in warm water. Emulsify 1:4 at 50°C to 60°C.

KEY PROPERTIES

MARDOL WT-47 is used as a single component anionic based stuffing wax for use in making stuffed or semi-stuffed leathers on both pasted and vacuum dried full grain and corrected leathers.

- Excellent single component pull-up wax
- Good holding properties for finish oil & wax applications
- Excellent emulsification and uniform distribution

APPLICATIONS

Recommended usage at 2% to 10%



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx