

Tannin™ Has It.

VITASOL 25

tannincorp.com

COMPOSITION

For the removal and further prevention of spew.

SPECIFICATIONS

Appearance	Dark liquid
Activity	100% (± 2)
Charge	Anionic
Density (Lb/Gal)	6.8 (± 0.2)
pH (10% Solution)	6.0 - 8.0
Solubility	Insoluble in water.
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Good
Electrolyte Stability	N/A
Emulsification	Not Soluble in Water.

KEY PROPERTIES

VITASOL 25 is made specifically for use on crusted or finished leather.

- Aids in the prevention of mold and fatty spews
- May not prevent mold, mildew, or spew from leather substance below and should not be considered a replacement for **VITASAN 10** in the wet end
- Can be added to and applied with a finish coat; it is necessary to experiment with the mixing procedure to ensure stability
- Can be applied to crusted or finished leathers by swabbing, spraying, or oiling-off machine; it can be applied to the grain, flesh, or both depending upon the condition of the leather
- Most effective if the leather is preheated, sprayed, and hung to dry overnight
- Normal requirement is 4-6 gr./sq. ft. as is
- Product should not be diluted



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx